

CLOUD 9 SUPER CONTRACT

- CLOUD 9 CRUMB
- SUITABLE FOR BOTH CONTRACT AND DOMESTIC APPLICATIONS
- EXCELLENT FOR IMPACT SOUND REDUCTION
- EXCELLENT THERMAL INSULATION PROPERTIES
- RECOMMENDED AREAS OF USE

LUXURY CONTRACT AND DOMESTIC USE IN AREAS SUCH AS LIVING ROOMS AND BEDROOMS.

SUITABLE FOR STRETCH-FIT OR DOUBLESTICK APPLICATIONS

Manufactured in the UK to BS 5808:1991 & BS EN 14499:2015

STANDARD SPECIFICATIONS		
TOP SURFACE	Silver film with green printing	
BOTTOM SURFACE	Silver film	
NOMINAL THICKNESS	10.00 mm	
NOMINAL ROLL WEIGHT	25 Kg	55.1 lb
WEIGHT PER UNIT AREA	1659 g/M ²	49 oz/yd²
ROLL LENGTH	11.0 m	36.0 ft
ROLL WIDTH	1.37 m	54 in
GUARANTEE	Lifetime of the initial carpet installation (when used in recommended areas)	
CORE DENSITY	160 Kg/M ³	
PRODUCT DENSITY	166 Kg/M ³	

BS. 5808 : 1991 TEST RESULTS - BRITISH STANDARD FOR CARPET UNDERLAYS				
END USE CLASSIFICATION	BS.5808	L/U		
WORK OF COMPRESSION AFTER 1000 IMPACTS	BS.4098	>150 J/m ²		
RETENTION OF WORK OF COMPRESSION	BS.4098	>90 %		
LOSS IN THICKNESS AFTER STATIC LOADING	BS.4939	<5.00 %		
LOSS IN THICKNESS AFTER DYNAMIC LOADING	BS.4052	<5.00 %		
RESISTANCE TO CRACKING	BS.5808 (A)	Pass		

FIRE RESISTANCE TESTS			
HOT METAL NUT TEST	BS.4790	Pass - Low radius of effect	
		2	ÉMISSIONS DANS L'AIR INTÉRIEU

INDOOR AIR QUALITY TEST		EMISSIONS DANS L'AIR INTERIEUR
TESTED TO ISO16000		
FRENCH VOC EMISSION CLASS LABEL	A+	
		"Information sur fervices of demandion and the information of the substances volatiles dates Tair Informat, andreafeatir un toose de toxicité ar inhelitions, aux me deballe de cases etiers de A + Ories

OTHER RELEVANT TESTS			
THERMAL RESISTANCE (TOG RATING)	BS 4745	2.3 TOG	
IMPACT SOUND IMPROVEMENT INDEX		39-42 dB	
(Test/Rated to BS EN ISO 140-8 / BS EN ISO 717-2)			

ISSUE 3 14-NOV-17

DISCLAIMER

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball & Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.

